arXiv:1507.06252v2 [cond-mat.mtrl-sci] 19 Nov 2015

Metamaterials: *supra*-classical dynamic homogenization*

Mihai Caleap and Bruce W Drinkwater

Faculty of Engineering, University of Bristol, BS8 1TR, United Kingdom

Abstract

Metamaterials are artificial composite structures designed for controlling waves or fields, and exhibit interaction phenomena that are unexpected on the basis of their chemical constituents. These phenomena are encoded in effective material parameters that can be electronic, magnetic, acoustic, or elastic, and must adequately represent the wave interaction behaviour in the composite within desired frequency ranges. In some cases – for example, the low frequency regime – there exist various efficient ways by which effective material parameters for wave propagation in metamaterials may be found. However, the general problem of predicting frequency-dependent dynamic effective constants has remained unsolved. Here, we obtain novel mathematical expressions for the effective parameters of two-dimensional metamaterial systems valid at higher frequencies and wavelengths than previously possible. By way of an example, random configurations of cylindrical scatterers are considered, in various physical contexts: sound waves in a compressible fluid, anti-plane elastic waves, and electromagnetic waves. Our results point towards a paradigm shift in our understanding of these effective properties, and metamaterial designs with functionalities beyond the low-frequency regime are now open for innovation.

Introduction

Metamaterial research in the past decade offered an entirely new route to further enhance our capability to engineer material properties at will. Here, metamaterials are artificially fabricated structures (often periodic, *i.e.*, crystalline) which are designed so that they exhibit wave properties not observed with common materials, *e.g.*, they can, in theory, bend electromagnetic [1], acoustic [2], and even surface gravity waves [3] so as to achieve sub-wavelength focusing [4], create cloaks [5, 6], and attain shielding [7]. Other unexpected properties include artificial magnetism [8], negative permeability [9], negative refraction index [10], and hyperbolic dispersion [11], to name a few. Such materials have allowed us to gain unprecedented control over a range of electromagnetic/optical and acoustic wave phenomena. In many ways metamaterials parallel the development of photonic and phononic crystals (optical and acoustic analogues of semiconductors) which also rely on small-scale structures for their properties. However, the major difference lies in the sub-wavelength nature of metamaterial structure. This enables us to summarize their properties in terms of permittivity and permeability (ε, μ) for electromagnetic waves, or bulk modulus and mass density (κ, ρ) for acoustic waves, just as we would for any naturally occurring material. This is an enormous simplification for the design process, and research is now focusing on the realization of a new generation of metadevices [12] with novel and useful functionalities achieved by the structuring of functional matter on the sub-wavelength scale. Novel devices such as superlens [13], hyperlens [14], invisibility cloaks [15, 16], and plasmonic waveguides [17] have been fabricated and tested in the past few years. The technology behind such metadevices is fairly well established in the *low-frequency* regime where inclusions have sizes much smaller than the wavelength of operation. At these relatively low frequencies this is commonly obtained by assuming only monopole and/or dipole interactions, *e.g.*, by utilizing conducting materials shaped as dipoles [18] and split-ring resonators [19]. The existence of resonances poses a considerable challenge to classical effective medium theories. This is because their basic principle is to minimize the scattering in the quasi-static limit, while the local resonances occur most often at longer wavelengths.

Here, following these concepts, we develop and analyse a *supra*[1]-classical dynamic model of metamaterial response. There is an abundance of miscellaneous effective medium theories [1–3, 23–26], some quite recent [6, 27, 29]; many of these works claim to be valid not only in the quasi-static limit but also at finite frequencies *beyond* the long-wavelength limit: a situation that happens when the wavelength Λ is long in the host medium, while the wavelength in the particles, Λ_0, can be small. (This is in contrast to the quasi-static limit where both Λ and Λ_0 should be much larger than the size of the particles.) Such extension to finite frequencies is sometimes denoted as the dynamic effective medium theory. However, even this *dynamic* approximation relies exclusively on the monopolar and dipolar response of the scattering objects, which implicitly assumes long wavelengths. In this paper, this restriction is relaxed and the full effect of the ensemble of particles that constitute the effective medium is included, as higher diffraction orders are encompassed. This will allow the design of new metadevices working over a wider wavelength range. We shall illustrate this by solving a simple scalar problem in two dimensions, having applications not only in electromagnetics but also in acoustics and elasticity. The similarities between the equations of acoustics, elasticity and electromagnetics allow us to use some of the same techniques to solve problems in these seemingly disparate fields.

---

*Dedicated with gratitude to the memory of Prof Yves C Angel

[1] This word comes from Latin and means *above* or *beyond the limits of.*

View on classical homogenization

The theoretical approach to the field of metamaterials is provided through dynamic homogenization techniques which relate the microstructure of a composite to the frequency dependence of its effective properties. The majority of research interest in the area of metamaterials is restricted to *periodic* microstructures [30, 31] (as the arrangement of molecules according to solid-state physics) which admit Bloch (or Floquet) waves as solutions and many different numerical algorithms have been developed (see, *e.g.*, [32, 33]) for calculating the dispersive properties of these waves. A popular route to determining these parameters is by the use of retrieval methods [34, 35] where the assumption is that local effective properties may be used to define periodic composites. The retrieval method leads to the refractive index n and the wave impedance $\mathcal{Z}$, which defines the reflectivity of a semi-infinite slab. However, while simple in principle, such retrieval methods are limited to ordered arrays and often produce ambiguous results due to oversimplified initial assumptions of the bulk model [36].

Certainly engineers like structures and designs that follow some type of order. However, materials may be also amorphous and isotropic, and natural materials on the macroscopic level are quite often *random* in essence. It may well be that a random placement of complex particles would be enough to produce emergent properties in the overall wave response and therefore give us a sample of metamaterial [37]. The effective behaviour of metamaterials whose microstructure is random depends strongly on the governing statistics of the random distribution. Effective properties may be determined by using the self-consistent *effective medium* methods for which a substantial body of literature may be found. Although variants exist, these methods often consider the scattering problem of a coated particle embedded in a matrix which has the properties of the effective media. These properties are then determined by requiring the vanishing of the effective forward-scattering amplitude $f_0^{eff} = f_{\theta=0}^{eff}$ and as such are formally restricted to the low-frequency and long-wavelength ranges. For examples where this method has been applied to electromagnetic, acoustic and elastic waves, see [1–6]. Although the above self-consistent condition ($f_0^{eff} = 0$) is physically sufficient to describe the effective medium, two effective properties, *i.e.* $(\varepsilon_{eff}, \mu_{eff})$, cannot be determined 'simultaneously and uniquely' from the single condition. A supplementary condition is needed; this prevents the application of effective medium methods to finding dynamic effective properties. Note however that the above condition is sufficient for wave propagation in a metamaterial in which a single material constant is involved, *e.g.* in dielectric media. Another deficiency of many current enhancements of the effective medium methods is their failure to describe the influence of the spatial distribution of particles on the effective constitutive parameters. Such a description is possible in the framework of a self-consistent scheme called the *effective field* method [37] and our work is within the framework of this scheme. One of the principal results of the effective field approach was an adequate definition of the coherent wave and a proof that it obeys a wave equation, *i.e.*, a proof that, under certain conditions, a random distribution of scatterers can, for this purpose, be represented by an effective medium [40]. Most calculations proceed by assuming the existence of such an effective medium equation.

The subject of the present work is the macroscopic dynamic behaviour of the above composite medium, *i.e.*, random distribution of particles. More precisely, we shall describe a heuristic scheme for evaluating the effective properties of metamaterials. The approach is based on the idea that a certain effective field acts on each particle, as a consequence of the presence of the other particles; hence, the name *effective field* method. The framework we develop is based on the Fikioris-Waterman [41, 42] and Waterman-Pedersen [8] formalism to evaluate the coherent wave motion on both sides of a semi-infinite array of particles.[2] More specifically, we consider an averaged wave motion, where all possible configurations of particles are weighted by appropriate pair-correlation functions. In contrast to the effective medium methods, we derive a fully dynamic model for the effective constitutive parameters, which retains all the relevant information (particle geometry and physical parameters) provided by an expanded multipole solution. As a result, the theory discussed in the following is more complete and potentially more useful than previous approaches to derive effective material parameters.

Results

Here, we consider two specific polarizations in electromagnetism, transverse electric (TE) and transverse magnetic (TM). In addition, parallel to the electromagnetic example is the mathematically identical case of acoustics and anti-plane elasticity.

We then consider these as two dimensional problems. Indeed, exploiting the physics common to many types

---

[2] The later reference, is the earliest work to our knowledge to predict explicit relations for the effective bulk parameters $(\varepsilon_{eff}, \mu_{eff})$ in the dynamic range. The authors have also predicted negative frequency-dependent μ_{eff} at single-particle resonances although the plots only displayed the positive values. In fact, they only noted that "*the effective parameters vanish or diverge at certain frequencies*" without further comment, which suggests that the results were considered curious at that time. Currently it is common to have negative effective parameters, and much research on metamaterials is focused on this area.

TABLE I: Relationships among electromagnetic, acoustic and elastic material parameters.

	Electromagnetics^a		Acoustics	Elasticity
m	$\varepsilon^{\mathrm{TM}}$	μ^{TE}	ρ^{P}	$1/G$
d	μ^{TM}	$\varepsilon^{\mathrm{TE}}$	$1/\kappa$	ρ^{SH}

[a] Observe that the permittivity and permeability for a specific polarization can be related to a pair of acoustic and elastic constants. For instance, $\left(\varepsilon^{\mathrm{TE}}, \mu^{\mathrm{TE}}\right) \leftrightarrow \left(\rho^{\mathrm{SH}}, \rho^{\mathrm{P}}\right) \leftrightarrow (1/\kappa, 1/G)$.

of wave propagation, the idea of metamaterials has been implemented successfully for acoustic and elastic waves. Many of the conclusions drawn from photonics research directly apply to acoustic waves and acoustic metamaterials due to the essential similarity of the governing equations in the two cases. Realizing analogous results for elastic metamaterials is complicated by the fact that the governing equation for elasticity admits both longitudinal and shear wave solutions which are capable of exchanging energy between each other. However, anti-plane elasticity is a special state of deformation with just a single non-zero displacement field, similar to transverse electromagnetics. The governing equation common to electromagnetics, acoustics, and linear anti-plane elasticity is detailed in Appendix A.

Effective constitutive parameters depend on many factors including the intrinsic properties of the particles and the host matrix, their shape and topology. The latter determines how the particles are distributed in the matrix. The system considered in our study is composed of two isotropic phases: cylindrical particles of arbitrary shape randomly distributed in a host medium with propagation constant $k = \omega\sqrt{\mathsf{md}}$ for some (possibly complex) parameters (m, d) of the medium. Depending on the application, these material parameters could be, *e.g.*, compliance $(1/G)$ and density (ρ) for shear horizontal polarized elastic waves or permittivity (ε) and permeability (μ) in electromagnetism; a number of useful relationships among these parameters are summarized in Table I.

In Appendix B, we briefly review the effective field method. Subject to the quasi-crystalline approximation, two equations are obtained for which the effective wavenumber $\mathcal{K}$ of some coherent wave motion (either electromagnetic, acoustic, or elastic) and the effective impedance $\mathcal{Z}$, are given in implicit form. Note that, whereas the dispersion relation for $\mathcal{K}$ is polarization-independent, the effective impedance depends on the type of the incident wave. These equations are the starting point of all further developments. Observe that the particles have a size distribution and their relative positions are described by an arbitrary *cross-pair* distribution function g_{ij}. Also, the size distribution is represented by $\eta_j = \eta(a_j)$; here a_j is the radius of the circular surface circumscribing a particle, and η is the number of particles per unit area.

Without loss of generality, we next assume the particles are identical and have equal sizes $a_j \equiv a$. Here, we refer only to the final explicit solutions for the effective parameters m_{eff} and d_{eff}, which are expressed elegantly as

$$\frac{\mathsf{m}_{eff}}{\mathsf{m}} \simeq 1 + \widetilde{\mathsf{m}}_1 \frac{\epsilon}{2k^2} + \widetilde{\mathsf{m}}_2 \frac{\epsilon^2}{2k^2} + \mathcal{O}\left(\epsilon^3\right), \tag{1}$$

$$\frac{\mathsf{d}_{eff}}{\mathsf{d}} \simeq 1 + \widetilde{\mathsf{d}}_1 \frac{\epsilon}{2k^2} + \widetilde{\mathsf{d}}_2 \frac{\epsilon^2}{2k^2} + \mathcal{O}\left(\epsilon^3\right), \tag{2}$$

where $\epsilon = 4\pi\eta$. The scalar coefficients $(\widetilde{\mathsf{m}}_1, \widetilde{\mathsf{m}}_2)$ and $(\widetilde{\mathsf{d}}_1, \widetilde{\mathsf{d}}_2)$ are given in matrix notation by

$$\widetilde{\mathsf{m}}_1 = \mathbf{e}^t\mathbf{Q}\mathbf{e} - \mathbf{e}^t\mathbf{J}\mathbf{Q}\mathbf{e}, \tag{3a}$$

$$\begin{aligned} \widetilde{\mathsf{m}}_2 &= \mathbf{e}^t\mathbf{Q}\widetilde{\mathbf{R}}\mathbf{Q}\mathbf{e} - \mathbf{e}^t\mathbf{J}\mathbf{Q}\widetilde{\mathbf{R}}\mathbf{Q}\mathbf{e} \\ &\quad - \frac{1}{4k^2}\left[\left(\mathbf{e}^t\mathbf{Q}\mathbf{e}\right)^2 - \left(\mathbf{e}^t\mathbf{J}\mathbf{Q}\mathbf{e}\right)^2\right], \end{aligned} \tag{3b}$$

and

$$\widetilde{\mathsf{d}}_1 = \mathbf{e}^t\mathbf{Q}\mathbf{e} + \mathbf{e}^t\mathbf{J}\mathbf{Q}\mathbf{e}, \tag{4a}$$

$$\begin{aligned} \widetilde{\mathsf{d}}_2 &= \mathbf{e}^t\mathbf{Q}\widetilde{\mathbf{R}}\mathbf{Q}\mathbf{e} + \mathbf{e}^t\mathbf{J}\mathbf{Q}\widetilde{\mathbf{R}}\mathbf{Q}\mathbf{e} \\ &\quad - \frac{1}{4k^2}\left[\left(\mathbf{e}^t\mathbf{Q}\mathbf{e}\right)^2 - \left(\mathbf{e}^t\mathbf{J}\mathbf{Q}\mathbf{e}\right)^2\right]. \end{aligned} \tag{4b}$$

One can easily check that these equations are compatible when $\mathsf{m}_{eff}\mathsf{d}_{eff}\mathcal{K}^2 = \omega^2$. Incidentally, we obtain $\mathcal{K}^2 \simeq k^2 + \epsilon\mathbf{e}^t\mathbf{Q}\mathbf{e} + \epsilon^2\mathbf{e}^t\mathbf{Q}\widetilde{\mathbf{R}}\mathbf{Q}\mathbf{e} + \mathcal{O}\left(\epsilon^3\right)$, which is, as expected, the second order expansion in ϵ of the implicit wavenumber equation (B1). Note that all notations appearing in Eqs. (3) and (4) are introduced in the Appendix.

Results in classical multiple scattering theories are usually defined in terms of the *angular shape function* f_θ for scattering of a plane wave by a single particle. It is useful to render yet another form of the coefficients (3) and (4) in terms of f_θ. This is done by considering the line-like approximation: in addition to $\epsilon a^2 \ll 1$, we also require $kb \ll 1$. To render the results more tractable, the spatial distribution of particles is assumed to be isotropic and homogeneous, for which $g_{ij}(r) \equiv g(r) = \mathrm{H}(r - b)$. This describes a non-overlapping condition; here, g denotes a *pair*-correlation function, H is the Heaviside unit function, and $b = 2a$ is the diameter of the particles. Retaining only the leading order term in kb of the multiple scattering matrix $\widetilde{\mathbf{R}}$, and using the definition (C2) for f_θ, we obtain

$$\mathbf{e}^t\mathbf{Q}\widetilde{\mathbf{R}}\mathbf{Q}\mathbf{e} \cong -\frac{1}{4k^2}\mathcal{H}_0 \text{ and } \mathbf{e}^t\mathbf{J}\mathbf{Q}\widetilde{\mathbf{R}}\mathbf{Q}\mathbf{e} \cong -\frac{1}{4k^2}\mathcal{H}_\pi, \tag{5}$$

with

$$\mathcal{H}_\alpha = \frac{2}{\pi}\int_0^\pi \mathrm{d}\theta \cot(\theta/2) \tfrac{\mathrm{d}}{\mathrm{d}\theta}\mathcal{G}_\alpha^\theta \text{ and } \mathcal{G}_\alpha^\theta = f_\theta f_{\alpha-\theta}. \tag{6}$$

By means of these approximations, we can infer the following closed-form constitutive relations

$$\frac{\mathsf{m}_{eff}}{\mathsf{m}} \simeq 1 + \frac{\epsilon}{2k^2}\left(f_0 - f_\pi\right) + \frac{\epsilon^2}{8k^4}\left[\left(\mathcal{G}_0^\pi - \mathcal{G}_0^0\right) - \left(\mathcal{H}_0 - \mathcal{H}_\pi\right)\right], \tag{7}$$

$$\frac{\mathsf{d}_{eff}}{\mathsf{d}} \simeq 1 + \frac{\epsilon}{2k^2}\left(f_0 + f_\pi\right) + \frac{\epsilon^2}{8k^4}\left[\left(\mathcal{G}_0^\pi - \mathcal{G}_0^0\right) - \left(\mathcal{H}_0 + \mathcal{H}_\pi\right)\right]. \tag{8}$$

Apart from their dependence on k and ϵ (or η), the effective dynamic parameters ($\mathsf{m}_{eff}, \mathsf{d}_{eff}$) given by Eqs. (7) and (8) are all completely determined when the angular shape function f_θ for an isolated particle is known. If this scattering amplitude can be determined either analytically, numerically, or experimentally, then the effective medium equivalent to the artificial composite is *fully* described.

It is noteworthy that if one wants to study the behaviour of effective parameters at high concentrations (where such expansions may not be valid) the general implicit equations detailed in Appendix B should be used and/or more accurate pair correlation functions should be considered. Neither incident wave nor boundary conditions have entered yet in the above description. Consequently, the results admit several solutions corresponding to different polarization states. In Ref. [44] (section S1), the expansions (1) and (2) [or (7) and (8)] are specialized to electromagnetic, acoustic, and elastic scattering for long wavelengths ($a \ll \Lambda$). This provides an additional check on the correctness of the results obtained in this paper. A further check on the consistency of our method is provided in Ref. [44] (section S2). It is shown that the quasi-crystalline approximation is *self-consistent* and identical to coherent potential approximation [45] at least to second order in concentration, provided the effective parameters are identified as those derived in this section.

Discussion

While the limiting cases considered in Ref. [44] (section S1) perform a check of the theory we have presented, they neglect some important features of the effective field method. Therefore, we address this problem numerically in order to illustrate the dynamic behaviour of the effective parameters. In the following, the effective parameters ($\mathsf{m}_{eff}, \mathsf{d}_{eff}$) are calculated by using Eqs. (1) and (2), together with the Percus-Yevick pair-correlation function for hard disks [46].



FIG. 1: Sketch of the scattering of an electromagnetic wave by a circular cluster of cylindrical particles.

Example illustration

We consider a fibre bundle (or circular cluster of dielectric fibres with $\mu_0 = 1$) of effective radius r_{eff} in vacuum. A plane electromagnetic wave is incident on the fibre bundle. A sketch is shown in Figure 1. There are 68 circular fibres each of radius a randomly distributed in the cluster and their volume fraction is 10.88%. The refractive index of the fibres is $n_0(=\sqrt{\varepsilon_0})= 1.33 + 0.01\mathrm{i}$. Exact multiple scattering simulations[3] are compared with the effective medium model (*i.e.* equivalent homogeneous magneto-dielectric inclusion[4] with effective parameters ($\varepsilon_{eff}, \mu_{eff}$)). The multiple scattering results are averaged over different realizations of the fibres locations. With 500 realizations, the maximum error between the numerical model and the effective medium results is less that 0.5%, for the two cases illustrated.

Figures 2 and 3 show the spatial maps of the near-field electric field amplitude $|E_z|$ for two different incident wavelengths, $\Lambda = 2r_{eff}/5 = 10a$ and $\Lambda = 4r_{eff}/25 = 4a$, respectively. Figure 2 illustrates the response of the coherent wave regarding the topology of the fibre-bundle. As expected, the waves are insensitive to the relative locations of the fibres for long wavelengths. This is not the same for shorter wavelengths. A comparison of the results in Figure 3 indicates the agreement is excellent

---

[3] The analytical solution to Maxwell equations for scattering by multiple parallel cylinders has been described, *e.g.*, in Ref. [49].

[4] Note that, as expected, our results also predict an effective magnetic permeability μ_{eff} at finite frequencies (different from that in vacuum) in a system in which both the matrix and the particles are non-magnetic.



FIG. 2: Spatial maps of near-field electric field $|E_z|$ as a TE wave is incident from the left. Exact multiple scattering simulations for a single realization of fibres locations: left panels (A, C) – random array; right panels (B, D) – regular array. Top panels (A, B) – effective radius r_{eff} of the cluster is such that $\Lambda = 2r_{eff}/5 = 10a$; bottom panels (C, D) – $\Lambda = 4r_{eff}/25 = 4a$.



FIG. 3: Spatial maps of near-field electric field $|E_z|$ as a TE wave is incident from the left. Left panels (A, C) – average over 500 different realizations (of exact multiple scattering simulations); right panels (B, D) – equivalent homogeneous inclusion (single scattering result) with dynamic effective parameters. Top panels (A, B) – effective radius r_{eff} of the cluster is such that $\Lambda = 2r_{eff}/5 = 10a$; bottom panels (C, D) – $\Lambda = 4r_{eff}/25 = 4a$.

even for the high frequency case considered ($\Lambda = 4a$). It is particularly encouraging that the agreement is excellent even inside the circular cluster. Observe that the a regular arrangement of fibres produces a result that is closer to the effective cluster for long wavelengths, than is the result obtained with a random realization of the fibres locations. We should note that although the comparison in Fig. 3 is excellent, it may not always be so for other geometries of the fibre bundle. In a final section we detail various limitations and assumptions of our model and discuss other similar problems obtained previously.

Anisotropic metamaterials

It is of considerable interest to discuss the possibility of realizing anisotropic metamaterials, that is, the material parameters are not scalars but tensors, with their principle components taking different values. Different from the anisotropy property of the material itself, we shall examine anisotropy originating from geometric asymmetry and consider a random array of elliptic cylinders of material parameters $(\mathsf{m}_0, \mathsf{d}_0)$. The x- and y-axes are set in the directions of the semi-minor and semi-major axes of the elliptic cylinders, with respective radii a_x and a_y. Due to the geometric arrangement of the elliptic cylinders and the symmetry of the scattered fields, the x- and y-directions can therefore be seen as effective principal directions. Proceeding essentially as detailed in Ref. [44] (section S1), we obtain, in the quasi-static limit

$$\frac{\mathsf{m}_{eff,x}}{\mathsf{m}} \simeq 1 + 2\phi\mathcal{M}_x + 2\phi^2\mathcal{M}_x^2, \tag{9}$$

$$\frac{\mathsf{m}_{eff,y}}{\mathsf{m}} \simeq 1 + 2\phi\mathcal{M}_y + 2\phi^2\mathcal{M}_y^2, \tag{10}$$

$$\frac{\mathsf{d}_{eff}}{\mathsf{d}} \simeq 1 + \phi\mathcal{D}, \tag{11}$$

where $\phi = \pi\eta a_x a_y$ is the volume fraction of the elliptical cylinders. The coefficients $\mathcal{D}$ and $(\mathcal{M}_x, \mathcal{M}_y)$ are given by

$$\mathcal{D} = \frac{\mathsf{d}_0}{\mathsf{d}} - 1 \text{ and } \begin{pmatrix} \mathcal{M}_x \\ \mathcal{M}_y \end{pmatrix} = \frac{1}{2}\frac{(\mathsf{m}_0 - \mathsf{m})\,(a_x + a_y)}{\mathsf{m}_0\binom{a_x}{a_y} + \mathsf{m}\binom{a_y}{a_x}}. \tag{12}$$

Observe that if $a_x = a_y$ ($= a$, *i.e.*, circular cross section) then $\mathcal{M}_x = \mathcal{M}_y$ ($=\mathcal{M}$, see Ref. [44], section S1), and $\mathsf{m}_{eff,x} = \mathsf{m}_{eff,y}$. The results of Eqs. (9)-(11) show that only the effective property $\overleftrightarrow{\mathsf{m}}_{eff}$ is a tensor with principal components $\mathsf{m}_{eff,x}$ and $\mathsf{m}_{eff,y}$, whereas d_{eff} is a scalar. This is consistent with results obtained recently in Ref. [6], for electromagnetic waves in the quasi-static limit. However, these results should be consumed with prudence. We show that, in general, both $\overleftrightarrow{\mathsf{m}}_{eff}$ and $\overleftrightarrow{\mathsf{d}}_{eff}$ are tensors for arbitrary frequency and wavelength. To see this more clearly, let us consider the scattering of a TM wave by perfect electric conductive elliptic cylinders in vacuum[5]. From Table I, we infer that (m, d) corresponds to (ε, μ), for TM waves; appropriate identifications the resulting effective medium are implied. Figure 4 shows the effective permittivity $\overleftrightarrow{\varepsilon}_{eff}$ and permeability $\overleftrightarrow{\mu}_{eff}$ tensors. Only the real part of these parameters is presented for brevity. The volume fraction ϕ is fixed and equal to $6\pi\%$. It should be noted that the actual concentration $\phi = \pi\eta a_x a_y$ cannot exceed a_x/a_y in order to be consistent with our model, so

---

[5] This is equivalent to solving the Neumann boundary condition. In anti-plane elasticity, this condition corresponds to a cylindrical cavity with stress-free surface.



FIG. 4: Effective permittivity $\overleftrightarrow{\varepsilon}_{eff}/\varepsilon$ $(= \widetilde{\varepsilon}'_{eff} + \mathrm{i}\widetilde{\varepsilon}''_{eff})$ (top panels, A-C) and permeability $\overleftrightarrow{\mu}_{eff}/\mu$ $(= \widetilde{\mu}'_{eff} + \mathrm{i}\widetilde{\mu}''_{eff})$ (bottom panels, D-F) *versus* the wavelength for a TM-polarized field incident upon a random distribution of elliptical perfect electrical conductive cylinders, for various aspect ratios a_x/a_y. Left panels (A, D) – $a_x/a_y = 1$; middle panels (B, E) – $a_x/a_y = 0.75$; and right panels (C, F) – $a_x/a_y = 0.5$.

that $\phi = \pi\eta a^2 \le 1$ when $a_x = a_y$ $(= a)$. The figure is intended to illustrate the variations of $\overleftrightarrow{\varepsilon}_{eff}/\varepsilon$ and $\overleftrightarrow{\mu}_{eff}/\mu$ as the wavelength $\Lambda/\widetilde{a}$ varies on the horizontal axis, for several aspect ratios a_x/a_y; here, $\widetilde{a} = \sqrt{a_x a_y}$ is the geometric mean of the semi-minor and semi-major axes, a_x and a_y. Observe that in the quasi-static limit, for $\Lambda > 10\widetilde{a}$, where currently available model will be adequate, the principal components of $\overleftrightarrow{\mu}_{eff}$ are visibly equal, *i.e.*, $\mu_{eff,x} \simeq \mu_{eff,y}$, regardless of the ratio a_x/a_y. This is as expected, given Eq. (11). It is interesting that for shorter wavelengths $(\Lambda < 10\widetilde{a})$, $\mu_{eff,x}$ and $\mu_{eff,y}$ become increasingly distinct as the ratio a_x/a_y decreases from 1 to 0.5, an effect not predicted by the existing literature. This suggests a new route to the design of metamaterials with controllable anisotropic effective properties.

Conditions of applicability

The results in Figures 2 and 3 support the reliability of the effective material parameters resulting form the *supra*-classical dynamic homogenization procedure reported here. Note however that, although not apparent in the results, there is an approximation involved in replacing a finite-size heterogeneous composite with its homogenized equivalent, in addition to the reliability of the homogenization procedure (which ignores transition region complications at the interface $|x| \le a$ [41]). In practical terms, it means that for a finite sample of the random composite the applicability of dynamic homogenization not only depends upon the frequency under consideration but also upon the phase of the composite at the boundary of the sample. An effort to quantify such an approximation is described in Ref. [47]. Here, the approximation results from truncating interfaces of a finite (or semi-infinite) 1-D periodic composite, the later being replaced with what are essentially its effective dynamic properties in the infinite Bloch-wave domain. Other questions will need to be answered relating to the shape and size of the scattering boundary, the effect of increasing the number of particles, and how many realizations are required to determine both the near- and far-fields accurately. It is expected that as the bounded area increases, so does the uncertainty of the calculated field. An investigation in this direction is beyond the scope of the paper, however we refer the reader to the comprehensive numerical analysis (based on the quasi-crystalline approximation) reported in Refs. [48, 53]. The later references should come with a warning, as their analysis contains the implicit (and incorrect [54]) assumption that the dielectric permittivity is the only quantity of interest.

Finally, let us note that the effective material parameters derived in here (which are tensor values for anisotropic media) are not necessarily tied to the physical material parameters of any of the individual elements of the metamaterial. A rather critical survey discussing the link and the difference between these two concepts (*i.e.* effective *versus* characteristic material parameters), particularly for the case of Maxwell's equations, is presented in Ref. [55]. As evidenced in this survey and references therein, homogenization theories continue to attract attention and even controversy. It appears, from considering exact reflection coefficients at oblique incidence (if one assumes that Fresnel-like formulae are always valid), that any effective material parameters that can be introduced in any theory would depend on the angle of incidence; broadly speaking, they would depend on the type of illumination. This means that these effective properties do not necessarily relate solely to the bulk properties of the material itself; they can involve the material and the type of illumination. Relevant considerations in this direction are presented for periodic composites in Refs. [56, 57]. A retrieval method extended to the arbitrary orientations of the principal axes of anisotropy and oblique incidence was presented in Ref. [58]. A discussion regarding modelling of the coherent wave propagation from the knowledge of the material properties along the principal axes only is elaborated in Ref. [59].

To summarize, a self-consistent multiple scattering approach, which enables the dynamic homogenization of metamaterials in two dimensions is developed. The quasi-crystalline approximation is employed to break the hierarchy of increasing conditional probability densities, but otherwise the treatment is exact. In particular, the effective wavenumber and the effective impedance is obtained. These characteristics can then be used to determine the effective constitutive parameters of the homogenised material. Whether the resulting effective parameters represent a true bulk property of the metamaterial in the dynamic range is yet to be determined. The two natural approximations - dilute media and low frequency approximations - show consistency, and, moreover, the quasi-static limit gives results reminiscent of the laws of Maxwell Garnett [9], Ament [12], and Kuster and Toksöz [13], respectively for electromagnetic, acoustic, and elastic material parameters (see Ref. [44], section S1, for more details). The entire analysis described in this work is germane for alternative analytical procedures based on other scattering operators $\mathbf{Q}$ for an isolated particle. As shown in Ref. [44] (section S2), a fully self-consistent procedure may be based on a new kind of isolated scatterer problem. We have shown that the coherent potential approximation, used in many previous works, is only an approximation of this procedure to the first order in the concentration of particles.

The theory provided here offers exciting opportunities for researchers in different communities, ranging from seismic waves to the entire field of ultrasound research, and spanning radio frequency and optical engineering. In particular, metamaterial modelling in optics, physical acoustics, and condensed matter physics may benefit from a rigorous, compact model for estimating more accurate and anisotropic effective medium parameters that homogenize artificial media.

Acknowledgments

The numerical results were obtained using the computational facilities of the Advanced Computing Research Centre, University of Bristol - http://www.bris.ac.uk/acrc/.

Appendix

A. Governing equation

There are many examples of wave equations in the physical sciences, characterized by oscillating solutions that propagate through space and time while, in lossless media, conserving energy. Examples include the scalar wave equation (*e.g.*, pressure waves in a gas), Maxwell's equations (electromagnetism), Schrödinger's equation (quantum mechanics), elastic vibrations, and so on. From a mathematical viewpoint, all of these share certain common features. In the following, we shall briefly identify the similarities between three types of such waves, in two dimensions: electromagnetic waves, anti-plane elastic waves, and acoustic waves. Electromagnetic waves are quite different from acoustic and elastic waves in that they can travel through vacuum. However, from an algebraic perspective, all three types of waves can be described by a unique scalar equation and hence these disparate phenomena can be studied simultaneously. The prototype problem consists of the wave equation at fixed angular frequency ω

$$\nabla\cdot\left(\mathsf{m}^{-1}\left(\mathbf{r}\right)\nabla\psi\left(\mathbf{r}\right)\right)+\omega^{2}\mathsf{d}\left(\mathbf{r}\right)\psi\left(\mathbf{r}\right)=0, \tag{A1}$$

where $c=1/\sqrt{\mathsf{md}}$ is the phase velocity of the wave for some parameters $\mathsf{m}\left(\mathbf{r}\right)$ and $\mathsf{d}\left(\mathbf{r}\right)$ of the medium. In the above, the scalar wavefunction $\psi\left(\mathbf{r}\right)\mathrm{e}^{-\mathrm{i}\omega t}$ corresponds to some physical field.

The problem considered here is reduced to points in the x-y plane (*i.e.* the cross section plane of our scattering geometry), which in polar coordinates are $\mathbf{r}=(r,\theta)$; here, θ is measured from the positive x-axis. Let us first consider the two important modes for electromagnetic wave propagation: the transverse electric field and the transverse magnetic field. These modes are closely analogous to anti-plane shear in elastodynamics and to acoustic waves. Let us assume the medium is isotropic and has dielectric permittivity ε and magnetic permeability μ that are independent of z. A transverse magnetic (TM) field is a special solution of the Maxwell's equations that has the form $\mathbf{H}=\psi\left(x,y\right)\mathbf{i}_z$, and the electrical field $\mathrm{i}\omega\varepsilon\mathbf{E}=-\nabla\times\mathbf{H}=\frac{\partial\psi}{\partial y}\mathbf{i}_x-\frac{\partial\psi}{\partial x}\mathbf{i}_y$. A transverse electric (TE) field is another special solution of the Maxwell's equations that has the form $\mathbf{E}=\psi\left(x,y\right)\mathbf{i}_z$, whereby the magnetic field is given by $\mathrm{i}\omega\mu\mathbf{H}=\nabla\times\mathbf{E}=\frac{\partial\psi}{\partial x}\mathbf{i}_y-\frac{\partial\psi}{\partial y}\mathbf{i}_x$. Observe that simple knowledge of the scalar wavefunction ψ suffices for the determination of the x and y components of the electric and magnetic fields, for the two polarizations. Hence, Eq. (A1) is the governing wave equation for electromagnetic waves provided that $(\mathsf{m},\mathsf{d},\psi)\leftrightarrow(\varepsilon,\mu,H_z)$ for TM waves, and $(\mathsf{m},\mathsf{d},\psi)\leftrightarrow(\mu,\varepsilon,E_z)$ for TE waves. The general solution independent of z is a superposition of the TE and TM solutions. This can be seen by observing that the Maxwell's equations decouple under this condition and a general solution can be written as $(H_x,H_y,H_z)=(H_x,H_y,0)+(0,0,H_z)$, where the second term represents the TM solution. The first term is of course the TE solution because $\nabla\times(H_x,H_y,0)=(0,0,\frac{\partial}{\partial y}H_x-\frac{\partial}{\partial x}H_y)$, which implies $E_x=E_y=0$ as expected. Let us now consider the case of anti-plane shear strain which is a special state of deformation where the displacement field is given by $\mathbf{u}=\psi\left(x,y\right)\mathbf{i}_z$. This is an out-of-plane mode of deformation and is analogous to transverse electromagnetic wave propagation. In the linear regime, an isotropic elastic medium is characterized by its density ρ and the Lamé elastic constants $G\equiv\mu$ and λ: G is the shear modulus (notation used to distinguish from the permeability μ employed in electromagnetics) and $\lambda=\kappa-G$ where κ is the two dimensional bulk modulus. Hence, Eq. (A1) is the wave equation for anti-plane shear provided that $(\mathsf{m},\mathsf{d},\psi)\leftrightarrow(1/G,\rho,u_z)$. Shear waves that satisfy this equation are also called SH (shear horizontal) waves, particularly in seismology. Finally, let us consider the acoustic wave propagation in an isotropic medium. For an inviscid fluid or gas, the shear modulus G is zero – and λ is just the bulk modulus. In this case, replacing ψ with the pressure $p=-\kappa\nabla\cdot\mathbf{u}$, we obtain precisely the acoustic wave equation (A1) for P (or compressional) waves if $(\mathsf{m}, \mathsf{d}) \leftrightarrow (\rho, 1/\kappa)$.

In essence, the solutions of the three problems considered will lead to similar conclusions if we make the appropriate interpretation of the quantities involved.

B. Effective field method

Suppose that discrete particles of cylindrical geometry are randomly and uniformly distributed in a half-space defined by $\{x > 0\}$. The particles need not be circular, provided that each of them can be contained in a circumscribing circular surface of radius a_j (with an axis of revolution parallel to the z-axis); their number density is η_j. Both the particles and the matrix are made of isotropic materials. Let a plane wave $\psi = \exp\left[\mathrm{i}\left(kx - \omega t\right)\right]$ of unit amplitude propagate with wavenumber k in the matrix along the x-direction. When this wave propagates in the composite material, multiple scattering occurs. Either propagation or diffusion, or a combination of the two phenomena is observed, depending on the frequency as well as on the geometrical and material properties of the composite. Assuming that propagation occurs, one can describe the coherent wave motion in the composite by a complex-valued wavenumber $\mathcal{K}$. The fundamental equation for configurational averages of the exciting and total fields for scalar wavefunctions has been derived in detail in Refs. [40, 41, 53, 60]. The quasi-crystalline approximation [61] is used to truncate the hierarchy of equations (Foldy-Lax hierarchy) so that only the correlation between every two particles is considered. We obtain the implicit dispersion equation for the effective wavenumber $\mathcal{K}$ of the coherent wave $\exp\left[\mathrm{i}\left(\mathcal{K}x - \omega t\right)\right]$,

$$\mathcal{K}^2 = k^2 + \textstyle\sum_j \epsilon_j \mathcal{F}\left(a_j\right), \tag{B1}$$

where $\epsilon_j = 4\pi\eta_j$, and the effective scattering amplitude $\mathcal{F}$ is given by

$$\mathcal{F}\left(a_j\right) = \mathbf{e}^t \left(\mathbf{Q}_j^{-1} - \textstyle\sum_i \epsilon_i \mathbf{R}_{ij}\right)^{-1} \mathbf{e}, \tag{B2}$$

$\mathbf{e} = (1, 1, \dots)^t$ is a constant unit vector. The shorthand notation $\mathbf{R}_{ij} \equiv \mathbf{R}\left(b_{ij}\right)$ and $\mathbf{Q}_j \equiv \mathbf{Q}\left(a_j\right)$ has been used. The infinite square matrices $\mathbf{R}\left(b_{ij}\right)$ and $\mathbf{Q}\left(a_j\right)$, have elements

$$\mathcal{R}_{n\nu}\left(b_{ij}\right) = \frac{\mathcal{P}_{n-\nu}\left(\mathcal{K}b_{ij}\right) - 1}{\mathcal{K}^2 - k^2} + \mathcal{N}_{n-\nu}\left(\mathcal{K}b_{ij}\right), \tag{B3}$$

where $b_{ij} \geqq a_i + a_j$, and

$$Q_{n\nu}\left(a_j\right) = \frac{1}{\mathrm{i}\pi} \delta_{n\nu} T_n\left(a_j\right). \tag{B4}$$

Here, δ_{ij} denotes the Kronecker delta, and $\mathcal{P}_\ell$ and $\mathcal{N}_\ell$ are given by

$$\mathcal{P}_\ell\left(z\right) = \frac{\mathrm{i}\pi}{2}\left[z H_\ell^{(1)}\left(x\right) \tfrac{\mathrm{d}}{\mathrm{d}z} J_\ell\left(z\right) - x J_\ell\left(z\right) \tfrac{\mathrm{d}}{\mathrm{d}x} H_\ell^{(1)}\left(x\right)\right],$$

$$\mathcal{N}_\ell\left(z\right) = \frac{\mathrm{i}\pi}{2} \int_{b_{ij}}^{\infty} \mathrm{d}r \left[g_{ij}\left(r\right) - 1\right] r H_\ell^{(1)}\left(kr\right) J_\ell\left(zr/b_{ij}\right),$$

where J_ℓ and $H_\ell^{(1)}$ are the cylindrical Bessel and Hankel functions, respectively, and $x = kb_{ij}$. The function g_{ij} is the cross-pair distribution function of two particle species (with sizes a_i and a_j), and satisfies the non-overlapping condition: $g_{ij}\left(r\right) = 0$ for $r < b_{ij}$; also, if the distance between particles tends to infinity, then the correlation between their locations disappears, *i.e.*, $\lim_{r\to\infty} g_{ij}\left(r\right) = 1$. The scattering coefficients $T_n\left(a_j\right)$ in Eq. (B4) depend on frequency, size a_j, as well as on the properties of the particle and those of the matrix material; they are evaluated by imposing appropriate boundary conditions at $r = a_j$.

Equation (B1) follows directly from a Lorentz–Lorenz-type law, and is an exact expression for the effective wavenumber, subject to the quasi-crystalline approximation. It is of interest to note how various physical aspects are embedded in this equation. The scattering matrix $\mathbf{Q}$ describes the response of a single particle to a plane incident harmonic wave with wavenumber k, and contains all the scattering behaviour in terms of particle geometry and physical parameters. The effective wavenumber $\mathcal{K}$ only appears in the matrix $\mathbf{R}$, which is defined by the spatial arrangements of particles, and accounts for multiple scattering. Should the distribution of particles be regular, the quasi-crystalline approximation is exact, in which case the multiple-scattering matrix $\mathbf{R}$ can be reduced to a well known lattice sum.

The theory described above is now complete insofar as behaviour within the medium is concerned. It is also of interest, however, to calculate the effective impedance $\mathcal{Z}$, which defines the reflectivity of the half-space $\{x > 0\}$ - a quantity which may be measured directly. Following the derivations in Refs. [37, 41], the coherent reflected field $\langle\psi\rangle = \mathfrak{R}\exp(-\mathrm{i}kx)$ at the half-space boundary can be obtained explicitly, with the reflection coefficient defined as

$$\mathfrak{R} = \frac{-\sum_j \epsilon_j \mathcal{F}_\pi\left(a_j\right)}{4k^2 + \sum_j \epsilon_j \mathcal{F}_0\left(a_j\right)}. \tag{B5}$$

Here, $\mathfrak{R}$ represents the average (coherent) back-scattered amplitude at normal incidence in the domain $\{x < 0\}$. The effective scattering amplitudes, $\mathcal{F}_0$ and $\mathcal{F}_\pi$, correspond to coherent waves scattered in the forward and backward directions, respectively, and are given by

$$\mathcal{F}_0\left(a_j\right) = \mathbf{e}^t \mathbf{Q}_j \mathbf{v}_j \text{ and } \mathcal{F}_\pi\left(a_j\right) = \mathbf{e}^t \mathbf{J} \mathbf{Q}_j \mathbf{v}_j, \tag{B6}$$

where $\mathbf{J} = \{\delta_{n\nu}\cos n\pi\}$ is a diagonal infinite matrix. The infinite eigenvector $\mathbf{v}_j$, associated with the wavenumber equation, follows from an Ewald–Oseen-type extinction theorem, with the result

$$\mathbf{v}_j = \frac{2k}{\mathcal{K}+k}\left(\mathbf{I} - \textstyle\sum_i \epsilon_i \mathbf{Q}_j \mathbf{R}_{ij}\right)^{-1}\mathbf{e}, \tag{B7}$$

where $\mathbf{I}$ is a unit infinite matrix. Martin [62] has obtained a formula for $\mathfrak{R}$ for obliquely incident waves on a half-space of circular scatterers; it can be shown that at normal incidence the result in his Eq. (39) gives agreement with Eq. (B5). The behaviour of the fields across interfaces was also examined in Refs. [62–64]; It was found that the fields themselves are continuous but the slopes are discontinuous. Using the estimate for the slope discontinuity, effective constitutive parameters can be derived, as shown in Refs. [62, 64]. Equation (B5) is an exact formula for the reflection coefficient[6]; it can be used to determine effective parameters $(\mathsf{m}_{eff}, \mathsf{d}_{eff})$ uniquely. It is often assumed that the effective medium corresponding to the distribution of particles may be described as a homogeneous medium from the standpoint of coherent wave propagation – the homogenized equivalent having the effective dynamic properties of the composite. In the following, we shall use this analogy, whereby the reflection coefficient $\mathfrak{R}$ at the interface between the homogeneous medium and the homogenized equivalent, may be written (as is standard) in terms of impedances (resulting in a Fresnel-like formula).[7] Then, equating the result with Eq. (B5), the effective impedance $\mathcal{Z}$ can be explicitly calculated. As expected, the effective impedance is different for different polarizations. Two cases are possible, with the following results:

$$\mathcal{Z}^{\mathsf{m}} = \mathcal{Z}/z \text{ and } \mathcal{Z}^{\mathsf{d}} = z/\mathcal{Z}, \tag{B8}$$

where

$$\mathcal{Z} = z\frac{4k^2 + \sum_j \epsilon_j \left[\mathcal{F}_0(a_j) - \mathcal{F}_\pi(a_j)\right]}{4k^2 + \sum_j \epsilon_j \left[\mathcal{F}_0(a_j) + \mathcal{F}_\pi(a_j)\right]}. \tag{B9}$$

Here, $z = \sqrt{\mathsf{m}/\mathsf{d}}$ is the impedance of the matrix; the superscripts 'm' and 'd' correspond to different physical situations, as we shall see below. We can now state our most general expressions for the effective dynamic constitutive parameters $(\mathsf{m}_{eff}, \mathsf{d}_{eff})$,

$$\frac{\mathsf{m}_{eff}}{\mathsf{m}} = \frac{\mathcal{K}}{k}\mathcal{Z}^{\mathsf{m}} \text{ and } \frac{\mathsf{d}_{eff}}{\mathsf{d}} = \frac{\mathcal{K}}{k}\mathcal{Z}^{\mathsf{d}} \tag{B10}$$

where $(\mathcal{Z}^{\mathsf{m}}, \mathcal{Z}^{\mathsf{d}})$ are defined in Eqs. (B8)-(B9). Observe that, by using the definition,

$$\mathcal{K} = k + \frac{1}{2k}\textstyle\sum_j \epsilon_j \mathcal{F}_0(a_j) \tag{B11}$$

in Eq. (B10), the resulting parameters $(\mathsf{m}_{eff}, \mathsf{d}_{eff})$ can be expressed explicitly in terms of the effective forward and back-scattering shape functions, $\mathcal{F}_0$ and $\mathcal{F}_\pi$.

To conclude this section, we consider the line-like approximation of the constitutive parameters (B10). For this, the size of the particles is assumed small compared to the incident wavelength ($a_j \ll \Lambda$). At leading order, the single-scattering operator $\mathbf{Q}$ is compact and has only three eigenvalues of finite size (related to terms with $n = 0, \pm 1$). Furthermore, the infinite multiple-scattering operator $\mathbf{R}$ is reduced to a rank 3 matrix. Omitting the details, we find for circular cylinders (with $T_1 = T_{-1}$),

$$\frac{\mathsf{m}_{eff}}{\mathsf{m}} \simeq \frac{k^2 + \frac{1}{\mathrm{i}\pi}\sum_j \epsilon_j T_1(a_j)}{k^2 - \frac{1}{\mathrm{i}\pi}\sum_j \epsilon_j T_1(a_j)}, \tag{B12}$$

$$\frac{\mathsf{d}_{eff}}{\mathsf{d}} \simeq 1 + \frac{1}{\mathrm{i}\pi k^2}\textstyle\sum_j \epsilon_j T_0(a_j). \tag{B13}$$

It can be shown that in the quasi-static limit ($a_j \ll \Lambda_0$) the effective property m_{eff} is reminiscent of the laws of Maxwell Garnett [11], Ament [12], and Kuster and Toksöz [13], in two dimensions, respectively for electromagnetic, acoustic, and elastic material parameters. (This is further described in Ref. [44], section S1.) On the other hand, the effective property d_{eff} reduces to the simple and inverse rules of mixtures, depending on the physical model under consideration, and as seen from Eq. (B13) is linear in ϵ_j.

C. Explicit second order approximations

At low concentrations ($\epsilon_j a_j^2 \ll 1$), the dispersion equation is explicit, and reduces to the well-known formula [40]

$$\mathcal{K}^2 \simeq k^2 + \textstyle\sum_j \epsilon_j f_0(a_j), \tag{C1}$$

where the forward-scattering amplitude f_0 is given by $f_0(a_j) = \mathbf{e}^t \mathbf{Q}_j \mathbf{e}$. More generally, the angular shape function f_θ for each particle is defined, in terms of Fourier series, as[8]

$$f_\theta(a_j) = \frac{1}{\mathrm{i}\pi}\sum_n T_n(a_j)\,\mathrm{e}^{\mathrm{i}n\theta}. \tag{C2}$$

---

[6] Note however that during the derivation, complications in the transition region $-a \leq x \leq a$ near and on both sides of the interface have been ignored [41].

[7] For instance, for acoustic waves $\mathfrak{R} = (\mathcal{Z} - z)/(\mathcal{Z} + z)$: this result implies the continuity of pressure and normal velocity at the interface; for anti-plane elastic waves $\mathfrak{R} = -(\mathcal{Z} - z)/(\mathcal{Z} + z)$: here, the continuity of the out-of-plane displacement and the corresponding stress are implicit. Similar results in electromagnetics are known as Fresnel relations (for TE and TM waves).

[8] Note the shorthand notation $\sum_n = \sum_{n=-\infty}^{\infty}$ is used throughout.

An expansion of the dispersion equation (B1) to the second order in concentration results in

$$\mathcal{K}^2 \simeq k^2+\textstyle\sum_j\epsilon_j\mathbf{e}^t\mathbf{Q}_j\mathbf{e}+\sum_{i,j}\epsilon_i\epsilon_j\mathbf{e}^t\mathbf{Q}_i\widetilde{\mathbf{R}}_{ij}\mathbf{Q}_i\mathbf{e}+\mathcal{O}\left(\epsilon_i\epsilon_j\epsilon_k\right), \tag{C3}$$

where the matrix $\widetilde{\mathbf{R}}_{ij} \equiv \widetilde{\mathbf{R}}\left(b_{ij}\right) = \lim\limits_{\mathcal{K}\to k}\mathbf{R}_{ij}$ and has elements

$$\begin{aligned}\widetilde{\mathcal{R}}_{n\nu}\left(b_{ij}\right) = \mathcal{N}_\ell\left(x\right) + \frac{\mathrm{i}\pi}{4k^2}\Big[&\left(\ell^2-x^2\right)J_\ell\left(x\right)H_\ell^{(1)}\left(x\right) \\ &- x^2\tfrac{\mathrm{d}}{\mathrm{d}x}J_\ell\left(x\right)\tfrac{\mathrm{d}}{\mathrm{d}x}H_\ell^{(1)}\left(x\right)\Big],\end{aligned} \tag{C4}$$

with $\ell = n-\nu$, and $x = kb_{ij}$. Note that for spatially uncorrelated particles, $\mathcal{N}_\ell\left(x\right)=0$.

For the effective impedance of Eq. (B9), at first order in concentration, we have

$$\mathcal{Z} = z - \frac{1}{2k^2}\textstyle\sum_j\epsilon_j f_\pi\left(a_j\right), \tag{C5}$$

where the back-scattering amplitude f_π is given by $f_\pi\left(a_j\right) = \mathbf{e}^t\mathbf{J}\mathbf{Q}_j\mathbf{e}$. The second order approximation is too long to warrant including here. For completeness, we also give the following results, in terms of Fourier series,

$$\mathbf{e}^t\mathbf{Q}_i\widetilde{\mathbf{R}}_{ij}\mathbf{Q}_j\mathbf{e} = \frac{\mathrm{i}}{\pi^2}\sum_{n,v}\widetilde{\mathcal{R}}_{n\nu}\left(b_{ij}\right)T_n\left(a_i\right)T_\nu\left(a_j\right), \tag{C6}$$

$$\mathbf{e}^t\mathbf{J}\mathbf{Q}_i\widetilde{\mathbf{R}}_{ij}\mathbf{Q}_j\mathbf{e} = \frac{\mathrm{i}}{\pi^2}\sum_{n,v}\left(-1\right)^n\widetilde{\mathcal{R}}_{n\nu}\left(b_{ij}\right)T_n\left(a_i\right)T_\nu\left(a_j\right). \tag{C7}$$

These expressions can be easily approximated in the low frequency limit by observing that, to leading order in (kb_{ij}), and for uncorrelated particles, $\widetilde{\mathcal{R}}_{n\nu} \cong \left|n-\nu\right|/2k^2$. The results obtained here have been used to derive the analytic formulae presented in the main text.

[1] Leonhardt, U. *Science* **312**, 1777–1780 (2006).
[2] Li, J., Fok, L., Yin, X., Bartal, G., and Zhang, X. *Nature Materials* **8**, 931–934 (2009).
[3] Porter, R. and Newman, J. *Journal of Fluid Mechanics* **750**, 124–143 (2014).
[4] Pendry, J. B. *Physical Review Letters* **85**, 3966–3969 (2000).
[5] Pendry, J. B., Schurig, D., and Smith, D. R. *Science* **312**, 1780–1782 (2006).
[6] Milton, G. W., Briane, M., and Willis, J. R. *New Journal of Physics* **8**, 248–248 (2006).
[7] Feng, S. and Halterman, K. *Physical Review Letters* **100**, 063901 (2008).
[8] Pendry, J., Holden, A., Robbins, D., and Stewart, W. *IEEE Transactions on Microwave Theory and Techniques* **47**, 2075–2084 (1999).
[9] Smith, D., Padilla, W., Vier, D., Nemat-Nasser, S., and Schultz, S. *Physical Review Letters* **84**, 4184–4187 (2000).
[10] Shelby, R. A., Smith, D. R., and Schultz, S. *Science* **292**, 77–79 (2001).
[11] Liu, Z., Lee, H., Xiong, Y., Sun, C., and Zhang, X. *Science* **315**, 1686 (2007).
[12] Zheludev, N. I. and Kivshar, Y. S. *Nature Materials* **11**, 917–924 (2012).
[13] Zhang, X. and Liu, Z. *Nature Materials* **7**, 435–441 (2008).
[14] Lu, D. and Liu, Z. *Nature Communications* **3**, 1205 (2012).
[15] Landy, N. and Smith, D. R. *Nature Materials* **12**, 25–28 (2013).
[16] Zigoneanu, L., Popa, B.-I., and Cummer, S. A. *Nature Materials* **13**, 352–355 (2014).
[17] Barnes, W. L., Dereux, A., and Ebbesen, T. W. *Nature* **424**, 824–830 (2003).
[18] Pendry, J., Holden, A., Stewart, W., and Youngs, I. *Physical Review Letters* **76**, 4773–4776 (1996).
[19] Pendry, J., Holden, A., Robbins, D., and Stewart, W. *IEEE Transactions on Microwave Theory and Techniques* **47**, 2075–2084 (1999).
[20] Li, J. and Chan, C. *Physical Review E* **70**, 055602 (2004).
[21] Wu, Y., Li, J., Zhang, Z.-Q., and Chan, C. *Physical Review B* **74**, 085111 (2006).
[22] Wu, Y., Lai, Y., and Zhang, Z.-Q. *Physical Review B* **76**, 205313 (2007).
[23] Torrent, D., Hakansson, A., Cervera, F., and Sánchez-Dehesa, J. *Physical Review Letters* **96**, 204302 (2006).
[24] Mei, J., Liu, Z., Wen, W., and Sheng, P. *Physical Review Letters* **96**, 024301 (2006).
[25] Torrent, D. and Sánchez-Dehesa, J. *New Journal of Physics* **13**, 093018 (2011).
[26] Wu, Y., Mei, J., and Sheng, P. *Physica B: Condensed Matter* **407**, 4093–4096 (2012).
[27] Torrent, D., Pennec, Y., and Djafari-Rouhani, B. *Physical Review B* **90**, 104110 (2014).
[28] Zhang, X. and Wu, Y. *Scientific Reports* **5**, 7892 (2015).
[29] Savoia, S., Castaldi, G., Galdi, V., Alù, A., and Engheta, N. *Physical Review B* **91**, 115114 (2015).
[30] Yablonovitch, E. *Physical Review Letters* **58**, 2059–2062 (1987).
[31] Martínez-Sala, R., Sancho, J., Sánchez, J. V., Gómez, V., Llinares, J., and Meseguer, F. *Nature* **378**, 241–241 (1995).
[32] Ho, K., Chan, C., and Soukoulis, C. *Physical Review Letters* **65**, 3152–3155 (1990).
[33] Goffaux, C. and Sánchez-Dehesa, J. *Physical Review B* **67**, 144301 (2003).
[34] Smith, D. R., Schultz, S., Markoš, P., and Soukoulis, C. M. *Physical Review B* **65**, 195104 (2002).
[35] Fokin, V., Ambati, M., Sun, C., and Zhang, X. *Physical Review B* **76**, 144302 (2007).
[36] Woodley, J. and Mojahedi, M. *Journal of the Optical*

Society of America B **27**, 1016 (2010).

[37] Caleap, M., Drinkwater, B. W., and Wilcox, P. D. *New Journal of Physics* **14**, 033014 (2012).

[38] Jin, J., Liu, S., Lin, Z., and Chui, S. *Physical Review B* **80**, 115101 (2009).

[39] Jin, C. *Journal of the Acoustical Society of America* **132**, 615–620 (2012).

[40] Foldy, L. L. *Physical Review* **67**, 107–119 (1945).

[41] Fikioris, J. G. and Waterman, P. C. *Journal of Mathematical Physics* **5**, 1413 (1964).

[42] Fikioris, J. G. and Waterman, P. C., *Journal of Quantitative Spectroscopy and Radiative Transfer* **123**, 8 (2013).

[43] Waterman, P. C. and Pedersen, N. E., *Journal of Applied Physics* **59**, 2609 (1986).

[44] See Supplementary text for a check on the consistency of our method, and an alternative self-consistent procedure.

[45] Milton, G. W. *Communications in Mathematical Physics* **99**, 463–500 (1985).

[46] Adda-Bedia, M., Katzav, E. and Vella, D. *Journal Of Chemical Physics* **129**, 049901 (2008).

[47] Srivastava, A. and Nemat-Nasser, S. *Wave Motion* **51**, 1045–1054 (2014).

[48] Sarabandi, K. and Siqueira, P. R. *IEEE Transactions on Antennas and Propagation* **45**, 858–867 (1997).

[49] Felbacq, D., Tayeb, G., and Maystre, D. *Journal of the Optical Society of America A* **11**, 2526 (1994).

[50] Garnett, J. C. M. *Philosophical Transactions of the Royal Society A: Mathematical, Physical and Engineering Sciences* **203**, 385–420 (1904).

[51] Ament, W. S. *Journal of the Acoustical Society of America* **25**, 638 (1953).

[52] Kuster, G. T. and Toksöz, M. N. *Geophysics* **39**, 587–606 (1974).

[53] Siqueira, P. and Sarabandi, K. *IEEE Transactions on Antennas and Propagation* **44**, 1067–1077 (1996).

[54] Bohren, C. F. *Journal of the Atmospheric Sciences* **43**, 468–475 (1986).

[55] Simovski, C. R. *Journal of Optics* **13**, 013001 (2010).

[56] Smigaj, W. and Gralak, B. *Physical Review B* **77**, 235445 (2008).

[57] Markel, V. A. and Schotland, J. C. *Physical Review E* **85**, 066603 (2012).

[58] Castanié, A., Mercier, J.-F., Félix, S., and Maurel, A. *Optics Express* **22**, 29937 (2014).

[59] Caleap, M., Aristégui, C., and Poncelet, O. *Journal of the Acoustical Society of America* **133**, 17–24 (2013).

[60] Linton, C. M. and Martin, P. A. *Journal of the Acoustical Society of America* **117**, 3413 (2005).

[61] Lax, M. *Physical Review* **85**, 621–629 (1952).

[62] Martin, P. A. *Journal of the Acoustical Society of America* **129**, 1685–1695 (2011).

[63] Aguiar, A. R. and Angel, Y. C. *Mathematics and Mechanics of Solids* **11**, 196–215 (2005).

[64] Aristégui, C. and Angel, Y. C. *Wave Motion* **47**, 199–204 (2010).

[65] Born, M. and Wolf, E. *Principles of Optics: Electromagnetic Theory of Propagation, Interference and Diffraction of Light* (Cambridge University Press, 1999).

Supplementary text

S1. Consistency check

It is straightforward to expand the low-frequency formulae obtained in the Appendix. Instead, the expansions (1) and (2) [or (7) and (8)] are approximated for long wavelengths ($a \ll \Lambda$).

Small cylinders behave as a combination of a monopole (or a source) and a dipole: this is a generic situation, and the leading order contribution to the angular shape function f_θ only involves the scattering coefficients $T_0(\omega)$ and $T_1(\omega)$, *i.e.*

$$f_\theta \simeq \frac{1}{\mathrm{i}\pi}\left(T_0 + 2T_1\right)\cos\theta. \tag{S1}$$

The integrals in Eq. (6) reduce to

$$\mathcal{H}_0 = \frac{8}{\pi^2}T_1\left(T_0+T_1\right) \text{ and } \mathcal{H}_\pi = -\frac{8}{\pi^2}T_1^2. \tag{S2}$$

Finally, using these results, the effective parameters may then be expressed as

$$\frac{\mathsf{m}_{eff}}{\mathsf{m}} \simeq 1 + \epsilon\frac{2}{\mathrm{i}\pi k^2}T_1 - \epsilon^2\frac{2}{\pi^2k^4}T_1^2, \tag{S3}$$

$$\frac{\mathsf{d}_{eff}}{\mathsf{d}} \simeq 1 + \epsilon\frac{1}{\mathrm{i}\pi k^2}T_0, \tag{S4}$$

which agree to $\mathcal{O}\left(\epsilon^2\right)$ with the general estimates (B12) and (B13) in Appendix B, as expected. We can see that d_{eff} and m_{eff} are related to monopolar ($n = 0$) and dipolar ($n = 1$) scattering coefficients, respectively. Note that the results in Eqs. (S3) and (S4) need not correspond to the quasi-static limit, because wavelength (and 1/e length, if losses are present) within the particles is as yet arbitrary relative to the particle size. Many previous effective medium results [S1–S6] correspond to such dynamic approximations. If we further assume that the wavelength within the particles is small ($a \ll \Lambda_0$), it can be shown that to the leading order in (ka),

$$T_0 \simeq \frac{\mathrm{i}\pi}{4}k^2a^2\mathcal{D} \text{ and } T_1 \simeq \frac{\mathrm{i}\pi}{4}k^2a^2\mathcal{M}, \tag{S5}$$

where

$$\mathcal{D} = \frac{\mathsf{d}_0}{\mathsf{d}} - 1 \text{ and } \mathcal{M} = \frac{\mathsf{m}_0 - \mathsf{m}}{\mathsf{m}_0 + \mathsf{m}}. \tag{S6}$$

The quasi-static relations (S5) with coefficients (S6) hold for a variety of boundary value problems, equivalent across electromagnetics, acoustics, and elasticity. This includes the Neumann boundary condition by setting $\mathsf{d}_0 = \mathsf{m}_0 = 0$. As is well known, the Dirichlet condition is atypical, and special care is needed.[9] In electromagnetism, Dirichlet or Neumann boundary conditions (depending on the polarization in question) describe inclusions that are perfectly conducting.

In terms of $\mathcal{D}$ and $\mathcal{M}$, Eqs. (S3) and (S4) yield

$$\frac{\mathsf{m}_{eff}}{\mathsf{m}} \simeq 1 + 2\phi\mathcal{M} + 2\phi^2\mathcal{M}^2, \tag{S7}$$

$$\frac{\mathsf{d}_{eff}}{\mathsf{d}} \simeq 1 + \phi\mathcal{D}, \tag{S8}$$

where $\phi = \epsilon a^2/4$ ($= \pi\eta a^2$) denotes the fractional volume occupied by the particles. These equations reduce to different forms in the quasi-static limit depending on application. Let us now specialize them to electromagnetic, acoustic, and elastic scattering, in succession.

Electromagnetic waves

There is a vast literature describing the many approaches to calculate effective-medium electromagnetic parameters [S8], and many of the existing theories are closely related to models developed in the late 1800s and early 1900s. We note in particular the expressions for the effective permittivity ε_{eff} obtained in three dimensions by Maxwell Garnett [S9] and by Bruggeman [S10] that, in turn, are closely related to the older Lorentz–Lorenz formula for time-dependent electric fields and the Clausius–Mosotti equation for static fields [S11]. The Bruggeman formula has the special property that it treats the particles and the environment symmetrically. However, this results in a quadratic order in ϕ that is different from the expansion of Maxwell Garnett rule. Conversely, our result for ε_{eff} is consistent with the rule of Maxwell Garnett. Indeed, consider a mixture where small magneto-electric particles are embedded in a host environment of permittivity (permeability) ε (μ). The complex permittivity of the particles is ε_0 and their permeability is μ_0. Then, for TM waves, we have

$$\varepsilon_{eff}^{\mathrm{TM}} \simeq \varepsilon + 2\phi\varepsilon\frac{\varepsilon_0-\varepsilon}{\varepsilon_0+\varepsilon} + 2\phi^2\varepsilon\left(\frac{\varepsilon_0-\varepsilon}{\varepsilon_0+\varepsilon}\right)^2, \tag{S9}$$

$$\mu_{eff}^{\mathrm{TM}} \simeq \mu + \phi\left(\mu_0 - \mu\right). \tag{S10}$$

Should the incident wave be electric in nature, ε and μ would have been interchanged. In the language of the dielectric problem, Eq. (S9) is reminiscent of the Maxwell Garnett estimate (more precisely, a small-ϕ approximation of the Maxwell Garnett rule in two dimensions). On the other hand, the effective permeability of Eq. (S10) is given by a simple rule of mixtures.

---

[9] A particular feature of the Dirichlet problem is the presence of $\log ka$ in the asymptotics of the solution. The interpretation of this effect depends on the physical model under consideration. For investigations in this direction, see, *e.g.*, Ref. [S7].

Sound waves in a compressible fluid

In the acoustics context, consider a fluid-particle mixture and let (ρ, κ) and (ρ_0, κ_0) be mass densities and bulk moduli of their respective phases. The particle material can be, *e.g.* solid or fluid. Then,

$$\rho^{\mathrm{P}}_{eff} \simeq \rho + 2\phi\rho\frac{\rho_0-\rho}{\rho_0+\rho}+2\phi^2\rho\left(\frac{\rho_0-\rho}{\rho_0+\rho}\right)^2, \tag{S11}$$

$$\kappa_{eff} \simeq \left(\frac{1-\phi}{\kappa}+\frac{\phi}{\kappa_0}\right)^{-1}. \tag{S12}$$

The mass density ρ^{P}_{eff} is analogue to that obtained in three dimensions by Ament [S12] (more precisely, a small-ϕ approximation of the Ament-estimate in two dimensions). Equation (S12) is recognized as the Reuss average for the effective bulk modulus κ_{eff}.

Anti-plane elastic waves in a solid composite

Consider the elastodynamic problem of anti-plane shear scattering, and let the host and particles have shear moduli G and G_0, respectively. Again, the particles can be made of, *e.g.* solid or fluid material. For solid particles, we obtain

$$\frac{G}{G_{eff}} \simeq 1 + 2\phi\frac{G-G_0}{G+G_0}+2\phi^2\left(\frac{G-G_0}{G+G_0}\right)^2, \tag{S13}$$

$$\rho^{\mathrm{SH}}_{eff} \simeq \rho + \phi\left(\rho_0-\rho\right). \tag{S14}$$

The effective shear modulus G_{eff} is analogue to that obtained in three dimensions by Kuster and Toksöz [S13] (more precisely, a small-ϕ approximation of the Kuster-Toksöz estimate in two dimensions). Observe that the effective mass density ρ^{SH}_{eff} in the case of anti-plane elasticity is also given by a simple rule of mixtures.

S2. Self-consistent effective field method

Self-consistent methods for the problem of scalar wave propagation through a medium with many particles may be found in the works of Maxwell and Rayleigh. During more than a century, in a number of works, these methods were extensively developed and used for the solution of various wave propagation problems. The present general results may be recast in terms of a *dual-layer* scattering operator $\mathbf{Q}_{eff}$ corresponding to a coated particle embedded in an effective medium with the properties m_{eff} and d_{eff}. The coating is made of the original matrix material with the properties m and d. For simplicity, we assume the particles are circular cylinders and have equal sizes $a_j = a$. The radius c of their coating defines the volume fraction to be $\phi = a^2/c^2$. Note that the theory presented below is not limited to only these geometries but applicable, in principle, to any other particle shapes. From Eq. (B1), we consider the effective wavenumber at the second order in concentration as,

$$\mathcal{K}^2 = k^2_{eff} + \epsilon\mathbf{e}^t\mathbf{Q}_{eff}\mathbf{e} + \epsilon^2\mathbf{e}^t\mathbf{Q}_{eff}\widetilde{\mathbf{R}}_{eff}\mathbf{Q}_{eff}\mathbf{e} + \mathcal{O}\left(\epsilon^3\right), \tag{S15}$$

where the effective operator $\mathbf{Q}_{eff}$ corresponds to a coated particle excited by the coherent motion $\exp(\mathrm{i}k_{eff}x)$. The multiple-scattering matrix $\widetilde{\mathbf{R}}_{eff}$ is given by Eq. (C4), but with k replaced by k_{eff}. The self-consistent scheme now assumes that $\mathcal{K} = k_{eff}$. From a physical point of view this means that the coherent wavefield the composite medium coincides with the wavefield propagating in the effective medium. Hence, the medium can be considered as homogenized since there is no scattering in the outer effective medium. This results in the following non-linear equation for k_{eff},

$$\mathbf{e}^t\mathbf{Q}_{eff}\mathbf{e} = \epsilon\mathbf{e}^t\mathbf{Q}_{eff}\widetilde{\mathbf{R}}_{eff}\mathbf{Q}_{eff}\mathbf{e} + \mathcal{O}\left(\epsilon^2\right). \tag{S16}$$

It is thought that the use of the self-consistent scheme (S16) applied to the effective wavenumber (B1) can improve the accuracy of the results while the concentration of particles increases. Note that since $\mathbf{Q}_{eff}$ is a transcendental function of the unknown k_{eff}, explicit solutions can only be obtained subject to low-frequency approximation. Writing the dual-layer forward-scattering amplitude f^{eff}_0 of a coated particle, as $f^{eff}_0 = \mathbf{e}^t\mathbf{Q}_{eff}\mathbf{e}$, Eq. (S16) is then reduced to

$$f^{eff}_0 \cong -\frac{2\epsilon}{\pi^2k^2_{eff}}T^{eff}_1\left(T^{eff}_0+T^{eff}_1\right). \tag{S17}$$

The effective scattering coefficients T^{eff}_0 and T^{eff}_1 can be calculated in terms of ϕ $(= \epsilon a^2/4)$, as

$$T^{eff}_0 \simeq \frac{\mathrm{i}\pi}{4\phi}k^2_{eff}a^2\left[\frac{\mathsf{d}}{\mathsf{d}_{eff}}\left(1+\phi\mathcal{D}\right)-1\right], \tag{S18}$$

$$T^{eff}_1 \simeq \frac{\mathrm{i}\pi}{4\phi}k^2_{eff}a^2\frac{\left(1+\phi\mathcal{M}\right)\mathsf{m}-\left(1-\phi\mathcal{M}\right)\mathsf{m}_{eff}}{\left(1+\phi\mathcal{M}\right)\mathsf{m}+\left(1-\phi\mathcal{M}\right)\mathsf{m}_{eff}}, \tag{S19}$$

where $\mathcal{M}$ and $\mathcal{D}$ are defined in Eq. (S6). We find directly that $T^{eff}_1 = \mathcal{O}\left(\phi^3\right)$, if one uses the small-$\phi$ estimate (S7). More generally, without restriction on ϕ, we obtain $T^{eff}_0 = T^{eff}_1 = 0$, for the following effective parameters,

$$\frac{\mathsf{m}_{eff}}{\mathsf{m}} = \frac{1+\phi\mathcal{M}}{1-\phi\mathcal{M}}, \tag{S20}$$

$$\frac{\mathsf{d}_{eff}}{\mathsf{d}} = 1+\phi\mathcal{D}. \tag{S21}$$

Here, m_{eff} and d_{eff} are the quasi-static limits of Eqs. (B12) and (B13). This result is significant, since (S17) reduces to the *coherent potential approximation* of solid state physics, regularly used in electromagnetics, acoustics and elastodynamics, and is equivalent to $f_0^{eff} = 0$. The coherent potential approximation appears to be an approximation of the solution to Eq. (S17) to first order in concentration. This leads to two important conclusions. First, the application of the self-consistent scheme to the quasi-crystalline approximation does not change the result (*e.g.* we obtain the same effective wavenumber in both cases, if and only if the effective parameters derived in this paper are employed), and second, it reduces exactly to the coherent potential approximation, at least to second order in concentration. The later is in contrast with the findings of Ref. [S14], where the wrong effective parameter was employed in the self-consistent scheme, that is $\mathsf{m}_{eff} = \mathsf{m} + \phi\,(\mathsf{m}_0 - \mathsf{m})$ (describing the effective mass density of a fluid-particle mixture). Finally, let us note another important aspect of the self-consistent effective field method presented in this section. The new self-consistent scheme (S16) includes the influence of the spatial distribution of particles (through the matrix $\widetilde{\mathbf{R}}_{eff}$), whereas the coherent potential approximation does not.

[S1] Li, J. and Chan, C. *Physical Review E* **70**, 055602 (2004).

[S2] Wu, Y., Li, J., Zhang, Z.-Q., and Chan, C. *Physical Review B* **74**, 085111 (2006).

[S3] Wu, Y., Lai, Y., and Zhang, Z.-Q. *Physical Review B* **76**, 205313 (2007).

[S4] Jin, J., Liu, S., Lin, Z., and Chui, S. *Physical Review B* **80**, 115101 (2009).

[S5] Jin, C. *Journal of the Acoustical Society of America* **132**, 615–620 (2012).

[S6] Zhang, X. and Wu, Y. *Scientific Reports* **5**, 7892 (2015).

[S7] Movchan, A. B., Poulton, C. G., Botten, L. C., Nicorovici, N. A., and McPhedran, R. C. *SIAM Journal on Applied Mathematics* **61**, 1706–1730 (2001).

[S8] Waterman, P. C. and Pedersen, N. E. *Journal of Applied Physics* **59**, 2609 (1986).

[S9] Garnett, J. C. M. *Philosophical Transactions of the Royal Society A: Mathematical, Physical and Engineering Sciences* **203**, 385–420 (1904).

[S10] Bruggeman, D. A. G. *Annalen der Physik* **416**, 636–664 (1935).

[S11] Born, M. and Wolf, E. *Principles of Optics: Electromagnetic Theory of Propagation, Interference and Diffraction of Light.* (Cambridge University Press, 1999).

[S12] Ament, W. S. *Journal of the Acoustical Society of America* **25**, 638 (1953).

[S13] Kuster, G. T. and Toksöz, M. N. *Geophysics* **39**, 587–606 (1974).

[S14] Norris, A. N. and Conoir, J.-M. *The Journal of the Acoustical Society of America* **129**, 104–113 (2011).